



Mosites #10116 Viton® Sheet

Mosites #10116 is a 75 durometer low compression set premium grade Viton® compound. It has excellent resistance to aliphatic and aromatic hydrocarbons, chlorinated solvents, petroleum oils, fuels, ozone and weather, lubricants, and animal or vegetable oils. It has a service temperature range of -10° F to 400° F.

Mosites #10116 is not recommended for service in acids or hot water and steam. Mosites has other Viton® compounds that are recommended for these applications.

Viton® is not recommended for service in low molecular weight esters and ethers, ketones, certain amines, hot anhydrous hydrofluoric or chlorosulphonic acids and alkyl phosphate esters.

The physical properties shown below were obtained on molded 0.080 inch thick ASTM samples. They are typical of Mosites #10116 but they should not be used to set Quality Control Specification minimum requirements.

Typical Physical Properties	
Durometer (shore A).....	75
Tensile Strength (psi).....	1700
Elongation at Break (%).....	180%
Modulus at 100% Elongation (psi).....	1000
Tear Strength (ppi).....	185
Specific Gravity.....	1.85
Compression Set (%)..... (22 Hours at 350° F)	7%

