



**Mosites #2902 Aflas® Fluoroelastomer**

Mosites #2902 is a 75 durometer high temperature resistant Aflas® fluoroelastomer compound. It has excellent resistance to acids, bases, high pH corrosion inhibitors, sour gas and oil, high pressure steam and alcohols. It is unusual in that it also has fair resistance to aromatic solvents and fuels, as well as ketones and low molecular weight esters and ethers. It has a service temperature range of -10° F to 675° F.

Mosites #2902 is not recommended for service in chlorinated solvents, Freon refrigerant, and tetrahydrofurane solvent.

The physical properties shown below were obtained on molded 0.080 inch thick ASTM samples. They are typical of Mosites #2902 but they should not be used to set Quality Control Specification minimum requirements.

<b>Typical Physical Properties</b>	
Durometer (shore A) .....	75
Tensile Strength (psi) .....	2600
Elongation at Break (%).....	210%
Modulus at 100% Elongation (psi).....	1150
Tear Strength (ppi) .....	128
Specific Gravity .....	1.58
Compression Set (%)..... (22 Hours at 350° F)	31%