

MOSITES #14127- Commercial Grade

Mosites #14127 is a 70 durometer, commercial grade silicone rubber sheet with light fabric impression finish. The formulations meet the requirements of Mil-R-5847D and A-A-59588, Class IIA and IIB; AMS 3304. The compound has excellent resistance to weathering and ozone, good resistance to hot water and low pressure steam, alcohols, diethylene glycols and fair resistance to petroleum base oils. The service temperature range is from -80°F to 450°F.

Silicone polymer is not recommended for service in aromatic solvents, fuels, chlorinated solvents and acids.

The physical properties shown below were obtained on molded 0.080 inch thick ASTM samples. They are typical of Mosites #14127 Gray but they should not be used to set Quality Control Specification minimum requirements.

<u>Typical Physical Properties</u>	
Hardness (Shore A).....	70
Tensile Strength (psi).....	1125
Elongation at Break (%).....	275%
Modulus at 100% Elongation (psi).....	805
Tear Strength (ppi).....	65
Specific Gravity.....	1.30
Compression Set (%)..... (22 Hours at 350°F)	14%
Color.....	Gray