



Mosites #10138 Viton® Sheet

Mosites #10138 is a 75 durometer smooth finish specification grade Viton® compound. It meets the requirements of Mil-R-25897, Type II, Class I; AMS-7278E, Grade 75, and ASTM D-2000, 2HK 714. It has excellent resistance to aliphatic and aromatic hydrocarbons, petroleum oils, fuels, ozone and weather, chlorinated solvents, lubricants, and animal or vegetable oils. It has a service temperature range of -10° F to 500° F.

Mosites #10138 is not recommended for service in acids or hot water and steam. Mosites has other Viton® compounds for these applications.

Viton® is not recommended for service in low molecular weight esters and ethers, ketones, certain amines, hot anhydrous hydrofluoric or chlorosulphonic acids and alkyl phosphate esters.

The physical properties shown below were obtained on molded 0.080 inch thick ASTM samples. They are typical of Mosites #10138 but they should not be used to set Quality Control Specification minimum requirements.

Typical Physical Properties

Hardness (shore A)	76
Tensile Strength (psi)	1487
Elongation at Break (%)	317%
Modulus at 100% Elongation (psi)	806
Tear Strength (ppi)	162
Specific Gravity	1.88
Compression Set (%)	26%
(22 hours at 350 deg. F)	

P.O. Box 2115, Fort Worth, TX. 76113
Phone: 817-335-3451 Fax: 817-870-1564
WEB: www.mositesrubber.com Email: sales@mositesrubber.com