



Mosites Rubber Co. Inc.
PO Box 2115
Ft. Worth TX, 76113
Ph 817-335-3451
Fax 817-870-1564
E-mail: sales@mositesrubber.com

Mosites # 14324 Silicone

Mosites # 14324 is a 40 durometer, high strength silicone compound with a platinum catalyst cure system. It is a transparent elastomer with excellent elongation properties and low modulus values, which make it an ideal choice for deep, draw vacuum applications. Uncured sheet is offered in widths up to 54 inches. Cured, however is available in standard widths up to 72 inches and custom fabricated vacuum blankets much larger, quoted upon request. The product has a service temperature range of -100°F to +400°F.

The physical properties shown below were obtained on 0.080-inch thick molded ASTM samples. They are typical of Mosites # 14324 silicone rubber compound, but they should not be used to set Quality Control Specification minimum requirements.

Important note: Mosites #14324 uncured must be transported and stored in temperatures between 0 deg F and 40 deg F.

Typical Physical Properties

Hardness (Shore A)	40
Tensile Strength (psi)	1600
Elongation (%)	1100%
Modulus at 100% Elongation (psi)	170
Modulus at 300% Elongation (psi)	330
Tear Strength (ppi)	250
Specific Gravity	1.11
Compression Set % (22 Hours @ 350° F)	16%
Color	Translucent