

Mosites #651-50Y Forming Rubber

This compound has the best flex crack resistance of our Mosites #651 series of forming rubber compounds.

The physical properties shown below were obtained on 0.080-inch thick molded ASTM samples. They are typical of Mosites 651-50Y, but should not be used to set Quality Control Specification Limits.

<u>Typical Physical Properties</u>	
Hardness (shore A).....	64
Tensile Strength (psi).....	2120
Elongation (%).....	800%
Modulus at 300% Elongation (psi).....	689
Tear Strength (ppi).....	271
Specific Gravity.....	1.50
Color.....	Tan

www.mositesrubber.com sales@mositesrubber.com
 2720 Tillar St., Fort Worth, TX. 76113
 Phone: 817-335-3451 Fax: 817-870-1564